



Pigment Red 8 (Naphthol Red)

CI PR8 | C.I. No. 12335

CAS: 6410-31-7 | Form: Powder | Purity: > 99% | MW: 339.76 g/mol

SECTION 1 - PRODUCT IDENTIFICATION

Colour Index	CI PR8 C.I. No. 12335	Form	Powder
CAS Number	6410-31-7	Purity	> 99%
Molecular Wt.	339.76 g/mol	Shade	Medium Red
Chemical Class	Azo (Monoazo)	Opacity	Semi-transparent

SECTION 2 - PHYSICAL & CHEMICAL PROPERTIES

Specific Gravity	1.35-1.45 g/cm3	Appearance	Fine homogeneous powder
Oil Absorption	60-70 g/100g	Heat Resistance	160CC
pH Value	6.0-7.5	Lightfastness	4
Moisture/Vol.	<= 1% Max	Weatherfastness	N/A

SECTION 3 - PERFORMANCE & FASTNESS PROPERTIES

Lightfast. (Mass)	4	Acid Fastness	4
Lightfast. (Tint)	N/A	Alkali Fastness	3
Water Fastness	3	Weather (Mass)	N/A
Oil Fastness	3	Weather (Tint)	N/A
Heat Stability	160CC	Standard Pack	25 kg Bags

SECTION 5 - KEY FEATURES & PROPERTIES

- Good tinting strength & clean medium red shade
- Economical monoazo red for general applications
- Easy dispersion in oil and resin media
- Reliable batch-to-batch colour consistency
- Suitable for rubber and general industrial use
- Widely used cost-effective pigment red

SECTION 6 - RECOMMENDED APPLICATIONS

Printing Inks	Suitable
Decorative Paints	Suitable
Rubber Colouring	Suitable

SECTION 7 - PACKAGING, STORAGE & COMPLIANCE

Standard Pack	25 kg Bags
Storage	Cool and dry storage below 30CC in sealed containers.
Shelf Life	2 years from date of manufactu
Manufactured By	Kanani Dyes Chem LLP, Gujarat, India
Quality Std.	ISO 9001:2015 ISO 14001:2015 ISO 45001:2018
Compliance	REACH Compliant RoHS Compliant FSSAI Certified

For Samples, Technical Queries & Pricing:

sales@kananipigment.com | +91 88499 95971 | www.kananipigment.com | Gujarat, India